

41

MR1035-1273



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

1745
RECEIVED
JAN 20 2004
TC 1700

Applicant : Guiping Zhang, et al. :

Serial No. : 09/933,838

: Group Art Unit#1745

Filed : 22 August 2001

: Examiner: S. N. Tang Foster

Title : MODIFIED LITHIUM ION POLYMER
BATTERY

TRANSMITTAL LETTER
ACCOMPANYING SUBSTITUTE RESPONSE TO RESTRICTION
REQUIREMENT AND AMENDMENT

Mail Stop NO FEE
Honorable Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Sir:


Applicant, by the undersigned attorney hereby responds to the Notice of Non-Compliant Amendment mailed from the U.S. Patent and Trademark Office on 6 January 2004. Attached to this Transmittal Letter is a "Substitute Response to Restriction Requirement and Amendment" with the proper status identifier of Claims 1, 2 and 4.

Additionally, attached to this Transmittal Letter is a copy of the Notice of Non-Compliant Amendment.

Appln. No. 09/933,838
Reply to Office Action of 1/6/2004

It is now believed that the subject patent application has been placed in
condition for Examiner and such action is respectfully requested.

Respectfully submitted,
For: ROSENBERG, KLEIN & LEE


Morton J. Rosenberg
Registration No. 26,049

Dated: *14 Jan 2004*


Suite 101
3458 Ellicott Center Drive
Ellicott City, MD 21043
(410) 465-6678



04586

PATENT TRADEMARK OFFICE

MR1035-1273



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

RECEIVED
JAN 20 2004
TC 1700

Applicant : Guiping Zhang, et al. :
Serial No. : 09/933,838 : Group Art Unit#1745
Filed : 22 August 2001 : Examiner: S. N. Tang Foster
Title : MODIFIED LITHIUM ION POLYMER
BATTERY

SUBSTITUTE
RESPONSE TO RESTRICTION REQUIREMENT AND AMENDMENT

Mail Stop NO FEE
Honorable Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Sir:

Applicant, by the undersigned attorney hereby responds to the outstanding Official Action dated 21 May 2003. The outstanding Official Action was a Restriction Requirement and being filed concurrently with this Response and Amendment is a Request for Extension of Time of one month to respond with the requisite fee being paid.

This Amendment has been prepared in accordance with the revised format published in the Official Gazette of 25 February 2001 (Vol. 1297, No. 4). Please amend the above-referenced patent application as follows:

1. (currently amended) A modified lithium ion polymer battery, comprising a positive electrode sheet a, a negative electrode sheet b, and a separation membrane c, wherein said positive and negative electrode sheets a and b are formed by blending a binder with positive electrode powder and coating the resulting blend on a copper foil or an aluminum foil used as the collector, wherein said binder ~~can be~~ is prepared from the following three components:

- (a) 0.5 wt%~95 wt% of polyvinylidene fluoride;
- (b) 0.1 wt%~90 wt% of a modified polyacrylates;
- (c) 0.1 wt%~85 wt% of a modified polyethylene ~~or polydienes~~;

~~alone, or from any two of them in a proper ratio, or all of these three components in a proper ratio;~~ wherein said positive and negative electrode sheets are laminated with a separation membrane to form a overlap sheet or roll in a alternative and isolation manner; said positive and negative collectors are welded, respectively; and the whole laminate is assembled with an aluminum plastic membrane.

2. (currently amended) A polymer battery as in claim 1, wherein said separation membrane is a ~~non-porous polyalkylene oxide film or a film made by coating a blend of polyalkylene oxide and polyvinylidene fluoride (PVDF), or a micro-porous polypropylene film, or a three-layered composite film of polypropylene/polyethylene/ polypropylene.~~

3. (original) A polymer battery as in claim 2, wherein said separation membrane is produced from polymethyl methacrylate and polyvinylidene fluoride.

4. (currently amended) A polymer battery as in claim 1, wherein said modified polyacrylates is a substance made by co-polymerizing more than 60 wt% of a carboxylic acid or carboxylic acid ester as the major constituent ~~selected from~~ a group consisting of acrylonitrile, ~~2-ethylhexyl acrylate, acrylic acid, methacrylic acid, methyl acrylate, methyl methacrylate, ethyl acrylate, butyl acrylate, butyl methacrylate, ethyl acrylate, propyl acrylate, acrylamide, vinyl acetate, dodecyl acrylate, octadecyl acrylate, hydroxyethyl acrylate, hydroxypropyl acrylate,~~ itaconic acid and the like; and 0~40% of a second constituent being selected from styrene and butadiene, into a copolymer, and subsequently neutralizing part or all of the carboxylic groups on said copolymer.

5. (original) A polymer battery as in claim 1, wherein said active material used in the positive electrode of the modified lithium ion polymer battery according to the invention is a composite oxide of lithium and transition metals, such as LiCoO_2 , LiMn_2O_4 , LiNiO_2 , $\text{LiNi}_x\text{Co}_{1-x}\text{O}_2$ and the like; and the active materials used in the negative electrode of the modified lithium ion polymer battery according to the invention is carbon powder, such as mesophase carbon

micro-beads (MCMB), natural graphite and modified products thereof, petroleum coke and modified products thereof, as well as hard carbon materials.

6. (original) A polymer battery as in claim 1, wherein said electrolyte is prepared by mixing a lithium salt selected from the group consisting of LiPF_6 , LiAsF_6 , LiClO_4 , $\text{LiN}(\text{CF}_3\text{SO}_2)_2$, LiBF_4 , LiSbF_6 , LiCF_3SO_3 and the like; an organic solvent selected from the group consisting of ethylene carbonate, propylene carbonate, dimethyl carbonate, diethoxyethane, diethyl carbonate, dimethoxyethane, dipropyl carbonate and the like; and a co-polymer.

7. (original) A polymer battery as in claim 6, wherein the concentration of said lithium salt in said electrolyte is 0.1~2 M.